SEPARATOR FOR ALKALINE SECONDARY BATTERY

SEPARATOR FOR ALKALINE SECONDARY BATTERY

9 =1 . 11 . 11 . 1 . 1	
Patent Number:	JP10125300
Publication date:	1998-05-15
Inventor(s):	UMEHARA YUICHI
Applicant(s)::	JAPAN STORAGE BATTERY CO LTD
Requested Patent:	□ <u>JP10125300</u>
Application Number:	JP19960299572 19961024
Priority Number(s):	
IPC Classification:	H01M2/16; D01F6/04; D04H3/00; D06M14/14; H01M10/28
EC Classification:	
EC Classification:	
Equivalents:	

Abstract

PROBLEM TO BE SOLVED: To suppress a self-discharge by using a separator obtained by graft- polymerizing acrylic acid to fibers made by a melt-blow method with fused and softened polyolefin in an air current.

SOLUTION: A nonwoven fabric is produced with a polypropylene resin by so-called melt-blow method. A nonwoven fabric made of polyolefin fibers formed by the melt spinning method is thermally melted and attached onto the surface of the melt-blown nonwoven fabric to supplement the strength of this nonwoven fabric to obtain a composite-structure nonwoven fabric. This composite-structure nonwoven fabric is dipped in a mixed liquid constituted of water of 80wt.% serving as a solvent, benzophenone of 0.3wt.% serving as a polymerization initiator, and acrylic acid of 19.7wt.% serving as a vinyl monomer, ultraviolet rays are applied in the nitrogen atmosphere to graft- polymerize acrylic acid, then it is washed with water and dried to form the separator.

Data supplied from the esp@cenet database - I2